(Portions of text and tables not shown are unaffected by the errata)

### 1<sup>st</sup> through 7<sup>th</sup> PRINTING (November 7, 2014)

## CHAPTER 7 WALL COVERING

**Table R702.1(3)** 

## TABLE R702.1(3) CEMENT PLASTER PROPORTIONS, PARTS BY VOLUME


	CEMENT PLASTER TYPE		VOLUME OF			
COAT		Portland Cement Type I, II or III or Blended Cement Type IP, I (PM), IS or I (SM)	Plastic Cement	Masonry Cement Type M, S or N	Lime	AGGREGATE PER SUM OF SEPARATE VOLUMES OF CEMENTITIOUS MATERIALS <sup>b</sup>
	Portland or blended	1			<sup>3</sup> / <sub>4</sub> - 1 <sup>1</sup> / <sub>2</sub> <sup>a</sup>	2 <sup>1</sup> / <sub>2</sub> - 4
First	Masonry			1	<del>-1</del>	$2^{1}/_{2}$ - 4
	Plastic		1			21/2 - 4

(Portions of text and tables not shown are unaffected by the errata)

### 1<sup>st</sup> through 7<sup>th</sup> PRINTING (Posted: 09-26-13)

## CHAPTER 7 WALL COVERINGS

#### **FIGURE 703.2.2**



SUPPORT BY ROOF MEMBERS

FIGURE R703.7.2.2
EXTERIOR MASONRY VENEER SUPPORT BY ROOF MEMBERS

(Portions of text and tables not shown are unaffected by the errata)

1<sup>st</sup> and 2<sup>nd</sup> PRINTING (JULY 14, 2011)

## CHAPTER 7 WALL COVERING

#### **TABLE R703.4**

WEATHER-RESISTANT SIDING ATTACHMENT AND MINIMUM THICKNESS

				TYPE OF SUPPORTS FOR THE SIDING MATERIAL AND FASTENERS <sup>b,c,d</sup>					
SIDING MATERIAL	NOMINAL THICKNESS <sup>a</sup> (inches)	JOINT TREATMENT	WATER- RESISTIVE BARRIER REQUIRED	Wood or wood structural panel sheathing	Fiberboard sheathing into stud	Gypsum sheathing into stud	Foam plastic sheathing into stud	Direct to studs	Number or spacing of fasteners
Fiber cement panel siding <sup>q</sup>	5/16	Note q	Yes Note u	6d common corrosion- resistant nail <sup>r</sup>	6d common corrosion- resistant nail <sup>r</sup>	6d common corrosion- resistant nail <sup>r</sup>	6d common corrosion- resistant <del>(12</del> "	4d common corrosion resistant nail <sup>r</sup>	6" o.c on edges, 12" o.c on intermed. studs
Fiber cement lap siding <sup>s</sup>	5-16	Note s	Yes Note u	6d common corrosion- resistant nail <sup>r</sup>	6d common corrosion- resistant nail <sup>r</sup>	6d common corrosion- resistant nail <sup>r</sup>	6d common corrosion- resistant (12 "-X 0.0.113")nail <sup>f,v</sup>	6d common corrosion- resistant nail or 11 gage roofing nail	Note t

R703.11.2.2 Basic wind speed exceeding 90 miles per hour or Exposure Categories C and D.......adjusted for height and exposure using Section Table R301.2(3). The design.....

(Portions of text and tables not shown are unaffected by the errata)

### 1<sup>st</sup> and 2<sup>nd</sup> PRINTING (SEPTEMBER 14, 2009)

# CHAPTER 7 WALL COVERING

TABLE R703.4 WEATHER-RESISTANT SIDING ATTAHCMENT AND MINIMUM THICKNESS
Note w. Adhered masonrySections 6.1 and 6.3 of ACI530/ASCE 5/TMS 402 TMS 402/ACI 530/ASC 5.